

Testing conditions:

Printability tester	AIC2-5	art.nr. 414
Printing disc	covered with screened copper strip, 50 mm wide, screen ruling: 25 l/cm 40 l/cm 60 l/cm	art.nr. 402.036.001 art.nr. 402.036.002 art.nr. 402.036.003
Printing force	625 N	
Printing speed	0.2 m/s, constant	
Packing	rubber	art.nr. 404.001.006
Ink	ink to be tested	
Ink film thickness on printing disc	2.4 ? m	

Method of operation:

1. Apply the ink to the inking unit, distribute the ink and ink the printing disc.
2. Make a print on the paper following the testing conditions as mentioned.
3. Judge the result visually (e.g. in comparison to an original print).

Dependent to the results it can be necessary to change the testing conditions.