IGT Information leaflet W55 TONER ADHESION constant speed, EN12283 IGT AIC2-5T2000, Global Standard Tester 2/3H Version: May 2017

 $8 \mu m (0.30 cm^3)$

Introduction

In laser printing/photocopying the toner is heated to have a good adhesion on the substrate. This adhesion is influenced by the type of printer, toner and paper. To use the printed documents the adhesion must be good. To check the adhesion a print with pick test oil can be made on the laser printed/photocopied substrate. It can be checked if the toner is pulled off from the surface.

In this leaflet W55 the method has been described for a constant speed of 0,4 m/s, according to EN 12283. If the toner is not pulled off from the paper and it must be known if there are differences in toner adhesion, the test can be carried out at higher constant speeds.

Another way to find out at what are the differences is to carry out the test at an increased speed so that the toner is pulled off at different levels. This method with increasing speed has been described in W56.

Principle

The paper is laser printed/photocopied. A strip of this toner printed paper is printed with pick test oil at a constant speed on an IGT printability tester. After printing the densities are measured at the location where the print has been made with pick test oil (toner has been pulled off) and at the location where no print has been made with the pick test oil (toner has not been pulled off). The densities are used in a formula to calculate the percentage of toner, which has been pulled off from the surface of the paper.

Method of operation

- It is recommended to execute the test in the standard atmosphere; to most standards it is 23,0 \pm 1,0 °C and 50 \pm 2% rh.
- For the operation of the AIC2-5T2000, Global Standard Tester, Inking Unit and ink pipette follow the instructions of the manuals, IGT information leaflet W100 and the displays accurately.
- Handle the samples carefully.

Preparation

- Condition the papers during > 6 hours in the standard atmosphere.
- 2. Print a stack of 10 sheets of a standard paper, the sheets of the papers to be tested and 5 sheets of the standard paper with a maximum density on a laser printer or photocopier.
- 3. Condition the papers, the pick test oil and the equipment during > 6 hours in the standard atmosphere.
- 4. Cut the paper strips (preferable 55*340 mm²), 5 strips per sample and mark them with top and/or bottom side, machine and/or cross direction and a code for the type of material.
- 5. Mount the packing on the sector. See W100.
- 6. For AIC2-5T2000 only:
 - 6.1. Adjust the printing force for the top printing disc shaft to 800 N and pay attention for the right backlash. See W100.
 - 6.2. Adjust the printing speed to 0,4 m/s in the constant speed mode (\square).
- For GST 2/3H only:
 - 7.1. Select the menu "Toner adhesion" in the display. For High Speed Inking Unit only (see note 2)

rol riigh speed liking Unit Only (see note 2).				
Adjust the unit with the following settings:				
	Water bath: 23,0 °C			
	Top roller: 4-segmented, rubber for conventional inks			
	Mode: 3			
	Startup time: 5 s			
	Distribution time: 30 s			
	Distribution speed: 0,5 m/s			
	2 nd distribution time: 10 s			
	2 nd distribution speed: 0,2 m/s			
	Inking time printing discs: 20 s			
NO	<u>TE</u> : Due to the temperature sensitivity of the pick test oil it is prefer			

to use the High Speed Inking Unit 4 with water bath above the inking unit AE FOUR.

Execution

Apply 0,30 cm³ of pick test oil to a segment of the top roller of the inking unit or add 0,03 cm3 of pick test oil to maintain this layer and distribute the pick test oil during the preset or desired time.

NOTE 1: Do not add pick test oil more than 4 times.

NOTE 2: For another type of top roller see the manual of the inking unit.

- Place the printing disc on the printing disc shaft of the inking unit and ink the printing disc during the preset or desired time.
- 3. If desired, adjust the printing speed of the tester.

36 (1 /T) / 1/2					
Materials / Testing conditions					
1	IGT AIC2-5T2000		710.000.000		
	or IGT Global Standard Tester 2		412.000.000		
	or IGT Global Standard Tester 3H		467.000.000		
2	IGT High Speed Inking Unit 4		466.000.710		
3	Top roller with 4 segments for con-	ventional inks	466.003.003		
4	IGT ink pipette		408.000.200		
5	Printing disc, aluminium, 20 mm		402.302		
6	Pick test oil, medium viscosity		404.004.020		
7	Packing, paper, 55 mm		404.001.005		
Phot	Photocopier or laser printer				
Den	Densitometer "Standard paper", 15 sheets A4 Paper to be tested, 5 sheets A4 per type				
"Sta					
Pape					
	Lint free rags and cleaning naphtha				
Printing force 800 N					
Printing speed Constant, 0,4 n		n/s			

- 4. Attach a test strip into the front clamp of the sector with the laser printed
- Take the printing disc from the inking unit and place it on the top printing disc shaft of the tester
- Make a print. See W100.
- Remove the test strip from the sector.

Pick test oil film thickness (volume)

Measure the test result as explained in the chapter "Assessment".

▶ The numbers 1 thru 7 are available at IGT Testing Systems

- Take the printing disc from the shaft and clean it with rags and naphtha and let it dry.
- 10. Repeat the points 1 thru 9 for every strip. It is recommended to perform the test at least 5 times per sample.
- 11. After having finished the tests, clean and store all parts as described in the
- 12. Make an accurate record of the conditions and the test results of the test and refer to W55.



Fig. 1: Toner adhesion

Assessment

- 1. Measure the densities on the toner which has not been subjected to the pick test (D solid black) and on the toner which has been subjected to the pick test (D _{IGT}). Measurements have to be made 10 times on every single strip.
- 2. Calculate the toner adhesion as:

Toner adhesion = (D $_{IGT}$: D $_{solid\ black}$) * 100% In which:

 D_{IGT} = density of toner which has been subjected to the pick test $D_{solid black}$ = density of toner which has not been subjected to the pick test

- 3. Repeat the points 1 thru 2 for every test strip.
- Calculate the average and if desired the standard deviation. Sometimes it can be useful to mention the highest and lowest values as well.

- 1. The maximum storage life of the pick test oil in the original, closed packing is 3 year; in an opened packing 1 year.
- ▶ 2006: In comparison to older IGT leaflets, this leaflet is valid for the AIC2-5T2000 and Global Standard Testers as mentioned.
- ▶ 2012: This leaflet is valid for the Amsterdam and AE FOUR as well and contains some small text corrections.
- ▶ 2017: This leaflet is valid for the AIC2-5T2000 and GST 2/3H only and contains some small text corrections.